



# AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A composition for preparing substances having a porous interlayer dielectric thin film, said composition comprising:


a ~~saccharide or saccharide derivative~~ one or more of a monomeric saccharide derivative or an oligomeric saccharide derivative which is selected from the group consisting of monomeric saccharide derivatives represented by the following formulas (8) to (10), disaccharide derivatives represented by the following formulas (11) to (13) and a polymeric saccharide derivative represented by the following formula (14):



(8)




(9)




(10)

---


in which R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> and R<sup>5</sup> are independently a C<sub>2-30</sub> acyl group.



(11)




(12)



(13)

in which,  $R^1, R^2, R^3, R^4, R^5, R^6, R^7$  and  $R^8$  are independently a  $C_{2-30}$  acyl group, or



(14)

in which  $R^1, R^2, R^3, R^4, R^5, R^6, R^7, R^8, R^9, R^{10}$  and  $R^{11}$  are independently a  $C_{2-30}$  acyl group;

a thermo-stable organic or inorganic matrix precursor; and

a solvent for dissolving both the ~~saccharide or~~ saccharide derivative and the matrix precursor.

2. (Currently Amended) The composition according to claim 1, wherein the content of the ~~saccharide or~~ monomeric and the oligomeric saccharide derivative is 0.1~95 wt.% of the solid components (the matrix precursor + the ~~saccharide or~~ saccharide derivative).

3. (~~Original~~Currently Amended) The composition according to claim 1, wherein the content of the solvent is 20.0~99.9 wt.% of the compositions (the matrix precursor + the saccharide ~~or saccharide derivative~~ + the solvent).


Claims 4-6 (Cancelled).

7. (Currently Amended) The composition according to claim 1, wherein the monomeric saccharide or oligomeric saccharide derivative is ~~selected from the group consisting of~~ glucose, glucopyranose pentabenzoate, glucose pentaacetate, ~~galactose, galactose pentaacetate, fructose, sucrose, sucrose octabenzoate, or sucrose octaacetate, maltose and lactose.~~

8. (Original) The composition according to claim 1, wherein the matrix precursor is silsesquioxane, alkoxysilane sol, or siloxane-based polymer.

9. (Original) The composition according to claim 8, wherein the silsesquioxane is hydrogen silsesquioxane, alkyl silsesquioxane, aryl silsesquioxane, or a copolymer thereof.

10. (Original) The composition according to claim 1, wherein the matrix precursor is a siloxane-based resin which is prepared by the hydrolysis and polycondensation of one or more monomers selected from the group consisting of compounds represented by the following formulas (1) to (4), using a catalyst and water in an organic solvent:




(1)

in which, R is a hydrogen atom, a C<sub>1-3</sub> alkyl group, a C<sub>3-10</sub> cycloalkyl group, or a C<sub>6-15</sub> aryl group;


X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> are independently a C<sub>1-3</sub> alkyl group, a C<sub>1-10</sub> alkoxy group, or a halogen atom, and at least one of them is a hydrolysable group;

p is an integer ranging from 3 to 8;


m is an integer ranging from 0 to 10; and



(2)



(3)




(4)

in which,  $X_1$ ,  $X_2$  and  $X_3$  are independently a  $C_{1-3}$  alkyl group, a  $C_{1-10}$  alkoxy group, or a halogen atom, and at least one of them is hydrolysable; and

n is an integer ranging from 1 to 12.

11. (Currently Amended) The composition according to claim 1, wherein the matrix precursor is a siloxane-based resin which is prepared by hydrolysis and polycondensation of a mixture of one or more monomers selected from the group consisting of compounds represented by the following formulas (1) to (4) together with one or more silane-based monomers selected from the group consisting of compounds represented by the following formulas (5) to (7) using a catalyst and water in an organic solvent:




(1)

in which, R is a hydrogen atom, a C<sub>1-3</sub> alkyl group, a C<sub>3-10</sub> cycloalkyl group, or a C<sub>6-15</sub> aryl group;


X<sub>1</sub>, X<sub>2</sub> and X<sub>3</sub> are independently a C<sub>1-3</sub> alkyl group, a C<sub>1-10</sub> alkoxy group, or a halogen atom, and at least one of them is a hydrolysable group;

p is an integer ranging from 3 to 8;


m is an integer ranging from 0 to 10; and



(2)



(3)



(4)

in which,  $\text{X}_1$ ,  $\text{X}_2$  and  $\text{X}_3$  are independently a  $\text{C}_{1-3}$  alkyl group, a  $\text{C}_{1-10}$  alkoxy group, or a halogen atom, and at least one of them is hydrolysable;

$n$  is an integer ranging from 1 to 12; and



in which  $\text{R}_1$  and  $\text{R}_2$  are respectively a hydrogen atom, a  $\text{C}_{1-3}$  alkyl group, a  $\text{C}_{3-10}$  cycloalkyl group, or a  $\text{C}_{6-15}$  aryl group; and

$\text{X}_1$ ,  $\text{X}_2$ ,  $\text{X}_3$  and  $\text{X}_4$  are independently a  $\text{C}_{1-3}$  alkyl group, a  $\text{C}_{1-10}$  alkoxy group, or a halogen atom.

12. (Original) The composition according to claim 10, wherein the content of the matrix precursor is more than 10 mol%.

13. (Original) The composition according to claim 11, wherein the content of the matrix precursor is more than 10 mol%.

14. (Original) The composition according to claim 11, wherein the mole ratio of the siloxane monomers having a cyclic or cage structure to the silane-based monomers is 0.99:0.01~0.01:0.99.

15. (Original) The composition according to claim 1, wherein the matrix precursor is a polyimide, polybenzocyclobutene, a polyarylene, or a mixture thereof.

16. (Original) The composition according to claim 1, wherein the solvent is an aromatic hydrocarbon-based solvent, a ketone-based solvent, an ether-based solvent, an acetate-based solvent, an amide-based solvent,  $\gamma$ -butyrolactone, a silicon-based solvent, or a mixture thereof.

17-21. (Canceled)

REMAINDER OF PAGE  
INTENTIONALLY LEFT BLANK